

## AK-ZG100

**Hardness: 60**

**Description:** Composite chromium carbide cladding layer, with very good wear resistance Impact resistance.

**Typical Chemical Composition(%):**

|               | C   | Si   | Mn   | Cr   | — | — | — | — | — |
|---------------|-----|------|------|------|---|---|---|---|---|
| Actual Result | 4.8 | 0.80 | 0.92 | 25.0 | — | — | — | — | — |

## AK-ZG101

**Hardness: 62**

**Description:** Composite chromium carbide boron carbide cladding layer, has very good wear-resistant and impact-resistant performance.

**Typical Chemical Composition(%):**

|               | C   | Si   | Mn   | Cr   | V    | Mo  | — | — | — |
|---------------|-----|------|------|------|------|-----|---|---|---|
| Actual Result | 5.0 | 0.85 | 0.89 | 26.0 | 0.80 | 1.0 | — | — | — |