



AKD-558-0

Deposited metal hardness:HRC 60-65

Application : Used in mining, cement, steel, electric power, coal processing. And other wear-resistant applications require industries. Suitable for wear-resistant surfaces that require anti-wear and wear resistance, such as the hammer head of the hammer mill, the cutter head of the road header and other components.

Typical Chemical Composition(%):

	C	Cr	Mn	Si	Other
Requirement	4.5-5.5	14.0-16.0	0.5-1.0	0.4-0.8	≤5.0

Recommended welding parameters:

Diameter /mm	1.2	1.4	1.6	— —
--------------	-----	-----	-----	-----