



AKD-60-0

Deposited metal hardness:HRC 58-64

Application :Used in cement industry, steel, electric power, mining, coal processing, and other wear-resistant industries. Suitable for wear plates, conveying channels, buckets, fans, fan blades, etc.

Typical Chemical Composition(%):

	C	Cr	Mn	Si	Other
Requirement	3.5-5.5	25.0-28.0	0.5-2.5	0.5-2.5	≤0.6

Recommended welding parameters:

Diameter /mm	2.4	2.8	3.2	—
--------------	-----	-----	-----	---