



AK-Z200WNi

Typical Chemical Composition(%): Hardness: 58-63

Element	C	Cr	Mn	Si	W	Ni	
Requirement (%)	3.0-5.0	22-28	0.5-2.5	0.5-2.5	3.0-5.0	1.0-3.0	

Used in cement, harbours, steel industry, mining, and other industries where wear-resistant use is required. Suitable for cone breakers, vertical mills/grinding discs, dredging buckets, screen plates, sand planers, top of dredging teeth.

AK-Z645

Typical Chemical Composition(%): Hardness: 57-62

Element	C	Cr	Mn	Si	W	Nb	Other
Requirement (%)	3.5-5.5	20-26	0.5-2.5	0.5-2.5	2.0-5.0	4.0-7.0	2.0-3.0

Applied in smelting, cement, petrochemical industry. Suitable for grate plate, calciner, crusher, converter, fan and so on.

AK-Z630

Typical Chemical Composition(%): Hardness: 20-25

Element	C	Cr	Mn	Si	Other		
Requirement (%)	0.5-1.5	14-17	13.0-16.0	0.5-2.5	1.0		

Used in cement industry, steel, electric power, mining, coal handling, and other industries that require wear-resistant usage. Suitable for bottoming repair of vertical mills, roller presses, etc.