



AK-Z688

Typical Chemical Composition(%): Hardness: 60-65

Element	C	Cr	Mn	Si	Other		
Requirement (%)	0.8-2.0	6.0-10.0	0.5-2.5	0.5-2.5	2.0		

Used in cement industry, steel, electric power, mining, coal handling, and other industries where wear-resistant use is required. Suitable for crusher rolls, bucket liners, etc. It can also be used for bottoming welding.

AK-Z888Ni

Typical Chemical Composition(%): Hardness: 58-64

Element	C	Cr	Mn	Si	Other		
Requirement (%)	3.0-4.5	25-29	0.5-2.5	0.5-2.5	1.5		

Used in cement industry, steel, electric power, mining, coal handling, and other industries that require wear-resistant usage. Suitable for chute, screen plate, conveying channel, bucket, mill liner, bucket liner, fan, fan blade.

AK-Z888

Typical Chemical Composition(%): Hardness: 58-64

Element	C	Cr	Mn	Si	Other		
Requirement (%)	3.0-4.5	25-29	0.5-2.5	0.5-2.5	1.0		

Used in cement industry, steel, electric power, mining, coal handling, and other industries that require wear-resistant usage. Suitable for chute, screen plate, conveying channel, bucket, mill liner, bucket liner, fan, fan blade.